



**PHASE II DRILL PROGRAM**  
**Montagne d'Or Gold Deposit**  
 Paul Isnard, French Guiana

**SIGNIFICANT RESULTS**

as at 2014-09-29

HOLE #	LENGTH (m)	SECTION		FROM	TO	Au (g/t)	Cu (ppm)	CORE LENGTH (m)	TRUE WIDTH (m)	METAL FACTOR	DESCRIPTION	ZONE
MO14157	185.0	2500E		156.8	168.6	1.19	705	11.8	9.2	11	T2, 1-10% py, tr-1% po, tr cp, loc. as s-m-s	LFZ
			Incl	165.8	168.6	2.42	1,032	2.8	2.3	5	T2, 5-15% py, 1-2% po, loc. as s-m-s	
MO14158	130.0	2700E	No significant values									
MO14159	130.0	2850E		36.0	49.3	1.31	250	13.3	10.4	14	T1, 1-10% py, tr-1% po, tr cp, loc. as s-m-s	LFZ
			Incl	36.0	37.0	12.22	401	1.0	0.8	10	T1, 5-15% py, loc. as s-m-s	
				69.1	86.7	0.53	222	17.6	13.8	7	T1, 1-5% py, 1-3% po, loc. as s-m-s	
MO14160	165.8	3400E		18.3	34.0	0.84	244	15.7	11.4	10	T1 SAP/SAPRK	UFZ
			Incl	27.0	32.0	1.46	277	5.0	3.7	5	T1 SAP/SAPRK, 1-2% py	
				49.0	59.0	1.69	286	10.0	7.7	13	T1, 5-8% py, tr po-cp	LFZ
			Incl	56.8	59.0	5.15	519	2.2	1.7	9	T1, 5% cp, 3% po, 1-2% py	
				118.0	127.2	1.59	180	9.2	7.4	12	T1, 1-3% py, tr-1% po-cp	
			Incl	123.5	125.4	3.56	327	1.9	1.5	5	T1, 2% py, 1% po, tr cp	
MO14161	158.0	3700E		9.0	26.0	0.84	389	17.0	12.9	11	T1, 1-10% py, loc. as s-m-s	LFZ
				47.0	52.0	3.93	78	5.0	3.8	15	V3, 1% po-cp	FWZ
				102.5	139.0	1.36	175	36.5	28.9	39	T1, 1-5% po, 1-3% py, tr-1% cp, loc. as s-m-s	
			Incl	110.0	115.0	5.45	525	5.0	4.0	22	T1, 4% py, 2-3% po, 1-2% cp	
				134.4	139.0	2.57	375	4.6	3.6	9	T1, 1-10% po, 1-3% cp, 1% py	
MO14162	198.0	4325E		5.0	21.0	1.78	822	16.0	11.9	21	V3 SAP/SAPRK	UFZ
				16.0	21.0	4.30	823	5.0	3.9	17		
MO14163	171.0	4275E	No significant values									
MO14164	266.0	2400E		153.0	165.9	1.50	447	12.9	11.6	17	T1, 3-10% py, tr-4% cp, tr-2% po, usually as s-m-s	HWZ
			Incl	154.8	157.0	4.85	643	2.2	2.0	10	T1, 4-5% py, tr-2% cp, tr po, usually as s-m-s	
				185.7	219.2	3.15	779	33.5	27.5	86	T1, 1-10% py, tr-2% cp, tr-1% po,	UFZ

				Incl	193.0	200.8	7.32	1,159	7.8	6.4	47	loc. as s-m-s		
												T1, 3-6% py, tr-1% cp, tr po		
MO14165	221.0	2500E		Incl	114.3	124.0	0.86	143	9.7	8.5	7	T1, 2-8% py, tr as-po-sp	HWZ	
				Incl	114.3	118.3	1.44	243	4.0	3.5	5	T1, 5% py, tr as		
					Incl	163.5	206.7	0.52	363	43.2	36.0	19	T1, 1-5% py, tr cp-po	UFZ
					Incl	175.5	183.9	1.01	756	8.4	7.0	7	T1, 3-4% py, tr cp-po	
MO14166	223.6	2810E			111.5	175.0	1.36	1,018	63.5	51.3	70	T1, 1-30% py, tr-30% cp, tr-10% po, loc. as s-m-s	UFZ	
					119.1	124.8	2.32	1,012	5.7	4.6	11	T1, 1-15% py, tr-1% po, tr cp, loc. as s-m-s		
					129.5	132.8	3.64	2,010	3.3	2.6	9	T1, 3-10% py, tr-2% po, tr cp, loc. as s-m-s		
					143.3	153.0	3.44	3,806	9.7	7.9	27	T1, 1-5% py, 1-10% po, tr-30% cp, loc. as s-m-s		
					162.4	168.7	2.12	807	6.3	5.2	11	T1, 1-5% py, tr-2% po, tr cp, loc. as s-m-s		
MO14168	242.0	2930E			106.2	176.0	1.16		69.8	54.5	63	T1, 1-10% py, 1-5% po, tr cp, loc. as s-m-s	UFZ	
					111.1	117.0	1.42	pending	5.9	4.5	6	T1, 1-4% py, tr-3% cp, tr-1% po		
					124.9	128.3	6.53		3.5	2.7	18	T1, 1-10% py, tr po-cp, as s-m-s		
					132.2	138.0	5.32		5.8	4.5	24	T1, 5-10% py, tr po-cp, as s-m-s		
MO14169	287.6	2850E			177.4	249.8	1.32		72.4	62.5	82	T1, 1-10% py, tr-2% po, tr-1% cp, loc. as s-m-s	UFZ	
					201.3	206.7	2.23	pending	5.4	4.7	10	T1, 1-5% py, tr-1% cp, as s-m-s		
					217.0	224.7	4.93		7.7	6.6	33	T1, 2-10% py, 1-2% po, tr cp, loc. as s-m-s		
					241.0	249.8	3.13		8.8	7.7	24	T1, 2-10% py, 1-2% po, tr-1% cp, loc. as s-m-s		
<b>Previously Announced Drill Holes (Phase II Drill Program)</b>														
MO13106	92.0	3490E			22.0	39.0	0.60	214	17.0	14.2	9	T1 SAP/SAPRK	LFZ	
MO13107	152.0	3540E			0.0	19.0	1.10	109	19.0	14.5	16	T1 SAPRK/SAP	UFZ	
				Incl	9.0	19.0	1.53	80	10.0	7.6	12			
					Incl	30.0	43.0	3.07	554	13.0	9.9	31	T1 SAP/SAPRK & V3 SAP	LFZ
					Incl	30.0	36.0	6.05	522	6.0	4.6	28		
						70.0	87.7	2.24	183	17.7	14.2	32	T1, 3-6% py, tr-2% po	
			70.0	78.0	3.58	206	8.0	6.4	23	T1, 4-6% py, tr-2% po	LFZ/ FWZ?			
			74.0	76.0	12.96	326	2.0	1.6	21					
MO13108	140.0	3490E			1.0	28.0	1.25	110	27.0	20.3	25	T1 SAP/SAPRK	UFZ	

			Incl	26.0	27.0	7.59	110	1.0	0.8	6	V3 SAP/T1 SAPRK	
				41.0	68.0	0.90	253	27.0	20.6	18	V3 SAP, T1 SAP/SAPRK & T1	LFZ
			Incl	41.0	50.0	1.60	407	9.0	6.8	11	V3 SAP & T1 SAP/SAPRK	
				61.4	68.0	1.32	327	6.6	5.1	7	T1, 1-2% py	
<b>MO13109</b>	122.0	3440E		1.0	29.0	0.73	94	28.0	21.8	16	T1 SAP/SAPRK	UFZ/LFZ
<b>MO13110</b>	110.0	3400E		5.0	33.5	1.51	503	28.5	21.6	33	T1 SAP	LFZ
			Incl	5.0	9.0	6.56	758	4.0	3.1	20		
<b>MO13111</b>	86.0	3350E		9.0	12.0	4.27	284	3.0	2.3	10	T1 SAP	LFZ
<b>MO14112</b>	108.7	3260E		57.1	64.5	0.83	118	7.4	5.8	5	T1, tr-2% py-po	LFZ
<b>MO14113</b>	118.0	3220E		52.5	64.0	1.18	207	11.5	9.2	11	T1, 1-10% py, tr-1% cp	LFZ/FWZ
			Incl	60.0	64.0	2.44	505	4.0	3.2	8		
<b>MO14114</b>	88.6	3170E	No significant values									
<b>MO14115</b>	167.0	3170E		107.2	116.0	3.47	741	8.8	6.7	23	T1, 1-25% py-po, tr-3% cp-as	LFZ
			Incl	112.0	116.0	5.13	195	4.0	3.0	16		
<b>MO14116</b>	149.0	3350E		18.0	37.3	0.91	476	19.3	14.5	13	T1 SAP/SAPRK & T1, 1-5% py	UFZ
			Incl	18.0	25.0	1.93	893	7.0	5.2	10	T1 SAP/SAPRK	
				67.1	78.8	3.35	716	11.7	9.1	30	T1, 1-10% py, 1-5% po, tr cp	LFZ
			Incl	67.1	70.0	11.70	2,635	2.9	2.3	27	T1, 5-15% py, 1-10% po, tr-1% cp	
				99.6	111.6	0.57	167	12.0	9.6	5	T1/I3B, 1-7% py, 1-10% po	
<b>MO14117</b>	161.0	3260E		54.0	63.0	1.14	1,023	9.0	7.2	8	T1, 1-2% py loc. as s-m-s	UFZ
				89.8	99.8	1.21	409	10.0	8.4	10	T1, 1-6% py, 1% po, loc. as s-m-s	
			Incl	92.0	96.0	2.33	355	4.0	3.3	8	T1, 1-6% py, 1% po, loc. as s-m-s, VG	
				120.0	145.0	0.62	124	25.0	21.4	13	T1, 1-5% py, 1% po	
			Incl	120.0	123.0	2.89	499	3.0	2.6	7	T1, 1-10% py loc. as s-m-s, 1% po	
<b>MO14118</b>	74.0	3100E		15.0	46.0	0.53	195	31.0	23.0	12	T1 SAPRK/SAP, T1 & I3B	LFZ
<b>MO14119</b>	143.0	3100E	No significant values									
<b>MO14120</b>	122.0	2930E		55.1	99.3	1.13	261	44.2	35.0	40	T1, 1-5% py-po	LFZ
				55.1	59.6	2.17	317	4.5	3.5	8	T1, 1-5% py-po, loc. as s-m-s	
			Incl	80.8	99.3	1.94	467	18.5	14.7	29	T1/I3B, 1-5% py-po, tr cp	
<b>MO14121</b>	110.5	2890E		59.0	75.9	1.93	287	16.9	13.2	25	T1/I3B, 1-5% py-po	LFZ
			Incl	72.0	75.9	7.08	796	3.9	3.1	22	I3B/T1, VG, 1-3% py, 1-2% po	
<b>MO14122</b>	111.6	2810E		16.0	31.0	0.58	308	15.0	11.5	7	T1 SAPRK/SAP	LFZ

MO14123	104.0	2750E	Incl	73.3	91.0	0.98	176	17.7	14.1	14	T1/I3B 1-5% py, tr po	LFZ
				73.3	76.9	2.72	317	3.6	2.9	8	I3B/T1, 1-15% py, tr po	
				86.9	91.0	1.75	206	4.1	3.3	6	T1, 1% py-po-as-cp	
MO14124	101.0	2700E		48.0	67.2	1.59	339	19.2	14.7	23	T1, 1-15% py, 1-5% po, tr as-cp, loc. as s-m-s	LFZ
MO14125	124.0	2650E		52.4	65.5	2.25	1,430	13.1	10.0	23	V3/T1, 1-10% py, 1% po, tr-1% as-cp, loc. as s-m-s	LFZ
				105.0	112.8	7.35	2,921	7.8	6.2	45	T1, 1-15% po, 1-5% py, tr-1% cp-as, VG	
MO14126	122.0	2600E	No significant values									
MO14127	98.0	2500E	Incl	80.0	90.0	5.28	665	10.0	7.8	41	T1, 1-15% po-py, tr% cp-as	LFZ
				80.0	82.2	14.45	767	2.2	1.7	25	T1, 1-30% po, 2-20% py, tr-1% cp-as	
				86.2	90.0	5.48	1,218	3.8	3.0	16	T1, 5-20% py, 1-10% po, tr-1% cp-as, loc. as s-m-s	
MO14128	123.0	2650E		16.0	29.0	0.85	583	13.0	10.2	9	T1, 1-5% py, tr cp-sp, loc. as s-m-s	UFZ
MO14129	122.0	3775E		79.8	92.0	0.92	593	12.2	9.7	9	T1, 1-15% py, tr-5% po, tr cp, loc. as s-m-s	FWZ
MO14130	98.0	3875E	Incl	10.0	38.2	0.81	732	28.2	21.5	18	T1 SAPRK/SAP & T1	UFZ
				10.0	16.0	1.26	229	6.0	4.7	6	T1 SAPRK/SAP	
				28.0	38.2	1.40	934	10.2	7.8	11	T1, 1-5% py, tr cp, loc. as s-m-s	
MO14131	98.0	3825E		43.0	50.7	1.53	569	7.7	5.9	9	T1, 1-5% py, tr-1% po-cp	LFZ
				48.1	50.7	2.40	443	2.6	2.0	5	T1, 1-10% py, 1% po, tr cp, as s-m-s	
MO14132	107.0	3925E	Incl	7.7	37.0	0.94	280	29.3	23.1	22	T1 SAPRK/SAP & V3 SAPRK	UFZ
				10.0	20.5	1.63	226	10.5	8.2	13		
				44.0	56.0	1.78	519	12.0	9.4	17	T1 SAPRK & V3 SAPRK	LFZ
	44.0	47.0	6.22	1,707	3.0	2.4	15	T1 SAPRK & V3 SAPRK , 1-10% py, tr-1% cp				
MO14133	122.0	3975E		36.0	56.0	0.65	541	20.0	15.0	10	V3 SAP & T1/V3/T2, 3-7% py, tr cp	LFZ
MO14134	111.0	4025E	Incl	33.3	55.6	2.80	959	22.3	17.2	48	T2, 1-3% py, tr cp-po-mt	LFZ
				33.3	40.9	3.29	692	7.6	5.8	19	T2 loc. V3, 1-3% py, tr cp-po-mt	
				46.4	55.6	4.01	1,629	9.2	7.1	29	T2, 1-5% py, tr-2% cp, tr po, loc. as s-m-s	
MO14135	131.0	4075E	Incl	59.0	64.4	1.97	1,373	5.4	4.2	8	V3, 1-4% po, 1-3% cp, 1% py	LFZ
				61.0	63.3	3.77	1,926	2.3	1.8	7		
				71.5	88.8	1.60	1,297	17.3	13.5	22	T2 & I3B, 1-5% py, 1-3% cp, 1-2% po	
	84.5	88.8	3.52	1,119	4.3	3.4	12	T2, 2-5% py, 1-2% cp, tr-2% po				
MO14136	101.0	4175E		74.1	78.6	2.51	1,111	4.5	3.5	9	T2, 5-10% py, 1-2% cp, tr-2% po, loc. as s-m-s	LFZ

<b>MO14137</b>	164.0	4225E		117.1	123.0	4.42	3,889	6.0	4.7	21	T2, 5-10% py, tr-2% cp-po, loc. as s-m-s	LFZ
<b>MO14138</b>	116.0	3590E	Incl	33.0	49.0	1.50	511	16.0	12.5	19	T1 SAP/SAPRK	LFZ
				45.0	49.0	2.94	442	4.0	3.1	9	T1 SAPRK	
<b>MO14139</b>	95.0	3540E		41.4	55.8	0.59	173	14.4	11.2	7	T1, tr-3% py, 1% cp, tr-1% po	FWZ
<b>MO14140</b>	134.0	4575E		56.5	62.6	1.75	582	6.1	4.8	8	V3 & T2, 5-15% py, 5-10% cp, 1-5% po, loc. as s-m-s	FWZ
<b>MO14141</b>	119.0	4675E		21.5	32.5	2.93	476	11.0	8.4	25	V3 SAPRK/SAP	LFZ
<b>MO14142</b>	170.0	4675E		135.0	144.8	1.08	845	9.8	7.4	8	V3 & T1, 1-20% py, 1-10% po, 1-5% cp, tr sp, loc. s-m-s	LFZ
<b>MO14143</b>	169.0	4525E	No significant values									
<b>MO14144</b>	158.0	4475E		14.0	17.0	3.41	2,058	3.0	2.3	8	V3 SAP	UFZ
<b>MO14145</b>	131.0	4375E		106.2	110.2	2.22	1,049	4.0	3.0	7	T1, 1-20% py, 1-2% po-cp, loc. as s-m-s	LFZ
<b>MO14146</b>	155.0	4425E	No significant values									
<b>MO14147</b>	101.0	4525E		61.1	72.0	0.57	94	10.9	8.2	5	V3 & T3, 1-2% py-cp-po, tr as	LFZ
<b>MO14148</b>	150.8	3010E	No significant values									
<b>MO14149</b>	164.0	2850E	Incl	42.5	82.0	1.85	1,270	39.5	29.2	54	T1, 1-10% py, 1-5% cp, loc. as s-m-s	UFZ
				76.9	82.0	9.02	6,385	5.1	3.8	34	T1, 10-30% py, 1-5% cp, loc. as s-m-s	
				103.0	108.0	1.39	860	5.0	3.8	5	T1, 1-10% py, 1-3% cp, loc. as s-m-s	
<b>MO14150</b>	161.0	2810E	Incl	16.0	61.6	1.38	448	45.6	34.9	48	T1 SAP/SAPRK & T1, 1-3% py	UFZ
				38.0	48.0	2.34	339	10.0	7.7	18	T1 SAP/SAPRK & T1, 1-2% py	
				54.0	60.6	4.73	1,796	6.6	5.1	24	T1, 1-5% py, tr-1% cp	
				80.0	91.5	1.75	1,291	11.5	9.0	16	T1, 1-3% py, 1-2% cp, tr-1% po	
<b>MO14151</b>	125.0	2400E	Incl	30.0	38.0	1.13	89	8.0	6.1	7	T1 SAPRK	UFZ
				51.0	99.2	0.94	418	48.2	37.0	35	T1, 1-10% py, tr po-cp, loc. as s-m-s	
				54.7	62.0	1.78	864	7.3	5.6	10	T1, 1-3% py, tr po	
<b>MO14152</b>	161.0	2500E	Incl	82.0	91.0	1.57	456	9.0	7.0	11	T1, 1-2% py, tr po-cp	UFZ
				40.0	51.3	1.80	90	11.3	8.6	15	T1 SAP/SAPRK	
				88.8	108.0	0.77	412	19.2	15.1	12	T1, 1-5% py, tr-1% cp, tr po, loc. as s-m-s	
<b>MO14153</b>	152.0	2700E	Incl	48.0	56.9	1.39	180	8.9	6.8	9	T1, 1-5% py, tr cp-po, VG	UFZ
				85.0	101.8	1.18	941	16.8	12.9	15	T1, 2-10% py, tr-1% cp-po, loc. as s-m-s	
				110.5	119.0	0.85	328	8.5	6.5	6	T1, 3-7% py, tr cp-po, loc. as s-m-s	
<b>MO14154</b>	155.0	2650E		138.2	151.0	6.49	pending	12.8	9.6	62	T1, 5-20% py, 1-5% po, 1% as, tr cp, loc. as s-m-s	LFZ

			Incl	142.0	147.9	13.45		5.9	4.4	59	T1, 10-20% py, 1-8% po, 1-3% as, tr-1% cp, loc. as s-m-s	
<b>MO14155</b>	173.0	2600E		18.0	27.0	0.87	pending	9.0	6.8	6	T1 SAP/SAPRK	UFZ?
				159.3	169.0	3.69		9.7	7.5	28	T1, 2-10% py, 1-3% po, tr cp-as, loc. as s-m-s	LFZ
			Incl	160.1	166.9	5.16		6.8	5.2	27	T1, 4-10% py, 1-4% po, tr cp-as, loc. as s-m-s	
<b>MO14156</b>	149.0	2400E		99.1	104.9	4.61	pending	5.8	4.3	20	T1, 3-10% py, 1% cp, tr po, loc. as s-m-s	LFZ
			Incl	99.1	102.0	7.52		2.9	2.1	16	T1, 5-15% py, 1-3% cp, tr po, loc. as s-m-s	

as: arsenopyrite / cp: chalcopyrite / po: pyrrhotite / py: pyrite / s-m-s: semi-massive sulphides / sp: sphalerite / tr: traces / VG: visible gold